

**BRITISH STANDARD**

---

**BS EN ISO  
3344 : 1997**

# **Reinforcement products — Determination of moisture content**

The European Standard EN ISO 3344 : 1997 has the status of a  
British Standard

ICS 59.100.01

**NO COPYING WITHOUT BSI PERMISSION EXCEPT AS PERMITTED BY COPYRIGHT LAW**

---



## National foreword

This British Standard is the English language version of EN ISO 3344 : 1997. It is identical with ISO 3344 : 1997.

The UK participation in its preparation was entrusted to Technical Committee PRI/42, Fibre reinforced thermosetting plastics and prepregs, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

### Cross-references

Attention is drawn to the fact that CEN and CENELEC Standards normally include an annex which lists normative references to international publications with their corresponding European publications. The British Standards which implement these international or European publications may be found in the BSI Standards Catalogue under the section entitled 'International Standards Correspondence Index', or using the 'Find' facility of the BSI Standards Electronic Catalogue.

**Compliance with a British Standard does not of itself confer immunity from legal obligations.**

### Summary of pages

This document comprises a front cover, an inside front cover, the EN ISO title page, the EN ISO foreword page, the ISO title page, page ii, page 1 to 5, a blank page, an inside back cover and a back cover.

This British Standard, having been prepared under the direction of the Sector Board for Materials and Chemicals, was published under the authority of the Standards Board and comes into effect on 15 July 1997

© BSI 1997

ISBN 0 580 27867 0

### Amendments issued since publication

Amd. No.	Date	Text affected

EUROPEAN STANDARD

EN ISO 3344

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 1997

ICS 83.120

Descriptors: see ISO document

English version

## Reinforcement products - Determination of moisture content (ISO 3344:1997)

Produits de renfort - Détermination du taux  
d'humidité (ISO 3344:1997)

Verstärkungserzeugnisse - Bestimmung des  
Feuchtegehaltes (ISO 3344:1997)

This European Standard was approved by CEN on 1997-05-10. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

# CEN

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

© 1997 CEN - All rights of exploitation in any form and by any means reserved worldwide for CEN national Members.

Ref. No. EN ISO 3344:1997 E

**Foreword**

The text of the International Standard ISO 3344:1997 has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1997, and conflicting national standards shall be withdrawn at the latest by November 1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

**Endorsement notice**

The text of the International Standard ISO 3344:1997 was approved by CEN as a European Standard without any modification.

**INTERNATIONAL  
STANDARD**

**ISO  
3344**

Second edition  
1997-05-15

---

**Reinforcement products — Determination  
of moisture content**

*Produits de renfort — Détermination du taux d'humidité*



\* S \*



Reference number  
ISO 3344:1997(E)

**EN ISO 3344 : 1997****Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3344 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*.

This second edition cancels and replaces the first edition (ISO 3344:1977), which has been technically revised.

**Descriptors:** plastics, reinforced plastics, reinforcing materials, textile glass fibres, carbon fibres, aramid fibres, reinforcement (structures), rovings, strands, mats, fabrics, tests, determination of content, humidity.

# Reinforcement products — Determination of moisture content

## 1 Scope

This International Standard specifies a method for the determination of the moisture content of reinforcement products, such as continuous-filament yarn, staple-fibre yarn, rovings, chopped strands, mats, fabrics and other forms of reinforcement made from textile glass, carbon or aramid fibres.

## 2 Normative reference

The following standard contains provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 291:—<sup>1)</sup>, *Plastics — Standard atmospheres for conditioning and testing.*

## 3 Definition

For the purposes of this International Standard, the following definition applies:

**3.1 moisture content:** The mass of water contained in a product, determined by a specified method and expressed as a percentage of the mass of the moist product.

## 4 Principle

A test specimen is weighed at ambient temperature, before and after drying at a temperature of 105 °C.

## 5 Apparatus

**5.1 Forced-circulation oven,** with an air-change rate of 20 to 50 times per hour and capable of maintaining a temperature of 105 °C ± 3 °C or the chosen temperature to within ± 3 °C (see clause 4).

**5.2 Desiccator,** containing a suitable drying agent (for example silica gel, calcium chloride or phosphorus pentoxide).

**5.3 Specimen holder,** made of heat-resistant material, allowing the maximum air flow round the specimen and from which there is no loss of material. This may be a porcelain crucible, an unoxidisable metal wire basket, etc.

NOTE — One holder may be used to hold several specimens if they can be transferred from the holder to the oven without loss of material.

---

1) To be published. (Revision of ISO 291:1977)

**5.4 Stainless-steel tweezers**, for handling the specimen and specimen holder.

**5.5 Balance**, accurate to 0,1 mg.

**5.6 Polished metal template and suitable cutting tool**, e.g. a knife, scissors or a rotary cutting disc (for fabrics and mats).

These two items may be replaced by a punch.

**5.7 Stoppered weighing bottle**, for weighing aramid yarn and when the specimen is expected to have a moisture content higher than 0,2 % (for example, specimens taken from the centre of a package or wet chopped strands).

## **6 Selection and number of test specimens**

### **6.1 Selection of specimens**

Unless indicated otherwise in the product specification or by the person requesting the determination, take the specimens as described below:

#### **6.1.1 Continuous-filament yarn, spun yarn, rovings**

The way in which the test specimens are taken is intended to enable the moisture content in the surface layers of the wound package to be checked.

Unwind and discard the outer layers, then, for each specimen, take a length of the wound package with a mass of at least 5 g, but preferably between 15 g and 30 g.

In cases when the moisture content of the wound package is liable to increase towards the centre, the product specification, or the person requesting the determination, may stipulate that the determination be carried out on one or more specimens taken at one or more specified locations within the package. Care should be taken to avoid injury when cutting into a package in order to reach the specimen position at the centre. Weigh specimens taken in this way as quickly as possible. For this purpose, the specimen may be placed in a previously weighed weighing bottle (5.7).

#### **6.1.2 Chopped strands and milled fibres**

Each specimen shall have a mass of at least 5 g, but preferably between 15 g and 30 g.

#### **6.1.3 Woven fabrics**

Take a piece of fabric of sufficient size to allow specimens of area 100 cm<sup>2</sup> to be obtained. If the mass of the specimen is less than 5 g, either take larger specimens or use several adjacent 100 cm<sup>2</sup> specimens.

Specimens may have the same dimensions as those used for the determination of the mass per unit area.

Do not take specimens at a distance of less than 10 mm from the edges or selvages of the fabric. If the specimen has to be folded, this shall not impede good air circulation round the whole specimen. It is recommended that specimens be cut out using a template and cutting tool, or with a punch (see 5.6), so as to avoid losing material.

#### **6.1.4 Mats**

The recommended specimen shape is that specified for the determination of the mass per unit area, i.e. a square cut out using a template of side 316 mm ± 1 mm. Other specimen shapes may be stipulated in the product specification or by the person requesting the determination.



## 6.2 Number of specimens

Unless indicated otherwise, the number of specimens taken from each elementary unit<sup>2)</sup> or laboratory sample<sup>3)</sup> shall be as specified in table 1.

Table 1

Reinforcement product	Number of specimens
Continuous or discontinuous filaments Rovings	1 specimen
Chopped strands Milled fibres	1 specimen
Woven fabrics Mats	3 specimens per metre width, spaced evenly across the width

The product specification or the person requesting the determination may stipulate that the determination be performed on a (specified) higher number of specimens which are generally taken from adjacent positions in the elementary unit or laboratory sample.

Moreover, it may be stipulated that the determination be repeated at different places within the elementary unit or laboratory sample.

## 7 Conditioning and test atmosphere

For products which are expected to have a moisture content below 0,2 %, condition the elementary unit or laboratory sample in a standard atmosphere as defined in ISO 291 for a time sufficient to reach equilibrium, usually a minimum of 6 h.

For products with a moisture content in excess of 0,2 %, carry out the determination rapidly after sampling, storing the elementary units or laboratory samples in a hermetically sealed container.

The material may be brought to standard temperature in the container prior to testing, but shall be sealed against moisture loss.

In addition, the sample shall, if applicable, be remixed within the container just prior to testing to avoid erroneous results which occur due to layering of the moisture within the material.

2) The elementary unit (as defined in ISO 1886:1990, *Reinforcement fibres — Sampling plans applicable to received batches*) is the smallest normally commercially available entity of a given product.

3) A laboratory sample is a part of the elementary unit from which the specimen(s) will be selected for the test. A laboratory sample is taken when it is impractical to bring the elementary unit into the test laboratory.

## 8 Procedure

The procedure described below is written for the case when the specimen is weighed in its holder. In the case when the specimen is weighed alone, proceed directly to 8.2 bearing in mind that the specimen is taken from the holder to weigh it and placed back in the holder using tweezers. Ensure that the specimens are placed in their holder at a location which can be identified throughout the procedure, and so that they do not touch each other.

### 8.1 Weighing the specimen holder

Stabilize the mass of the holder (5.3) by placing it in the oven (5.1), maintained, to within  $\pm 3$  °C, a temperature of 105 °C or, if the reinforcement product is known to contain volatile matter other than water which may escape at 105 °C, a lower temperature is chosen. However, the drying temperature chosen may be not below 50 °C. Handle the holder with tweezers (5.4).

Allow the holder to cool in the desiccator (5.2) to the appropriate standard temperature as defined in ISO 291.

Weigh the holder to the nearest 0,1 mg, recording the mass, in grams, as  $m_0$ .

### 8.2 Initial mass of specimen

Immediately after cutting out the specimen, place it in the holder.

Weigh the specimen and holder together to the nearest 0,1 mg, recording the mass, in grams, as  $m_1$ .

### 8.3 Final (dry) mass

Place the specimen and holder together in the oven maintained at a temperature of 105 °C  $\pm$  3 °C or at the chosen temperature  $\pm$  3 °C (see 8.1). Ensure that no specimen comes into contact with the sides of the oven. Use the tweezers to handle the specimens. Heat the specimen for at least 1 h to allow the mass of the specimen to reach a constant value.

On removal from the oven, immediately place the specimen in its holder in the desiccator for a minimum of 30 min, the desiccator being placed in a room at standard temperature (see ISO 291).

Weigh the test specimen plus holder together to the nearest 0,1 mg, recording the mass, in grams, as  $m_2$ .

## 9 Expression of results

Calculate the moisture content of each specimen  $H$ , as a percentage by mass, using the equation

$$H = \frac{m_1 - m_2}{m_1 - m_0} \times 100$$

where

$m_0$  is the mass, in grams, of the holder (this will be zero if the specimen is weighed without the holder);

$m_1$  is the initial mass, in grams, of the undried specimen (with or without holder);

$m_2$  is the final mass, in grams, of the dried specimen (with or without holder).

The result of the determination will be either the result obtained for one specimen (if only one specimen is examined per determination) or the average of the results obtained for each specimen taken for the determination.

## 10 Precision

The precision of this test method is not known because interlaboratory data are not available. Interlaboratory data are being obtained and a precision statement will be added at the next revision.

## 11 Test report

The test report shall include the following information:

- a) a reference to this International Standard;
- b) all details necessary for identification of the reinforcement product examined (as per the designation provided in the applicable product specification);
- c) the dimensions and mass of each specimen;
- d) the number of specimens examined;
- e) the individual result of each determination and, if required, the results for each specimen;
- f) details of any operation not specified in this International Standard, as well as any incident liable to have had an effect on the results.
- g) the date of the test.



\*  
5  
\*

---

## **BSI — British Standards Institution**

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

### **Contract requirements**

A British Standard does not purport to include all the necessary provisions of a contract. Users of British Standards are responsible for their correct application.

### **Revisions**

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the responsible technical committee, the identity of which can be found on the inside front cover. Tel: 0181 996 9000; Fax: 0181 996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

### **Buying standards**

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services, Sales Department at Chiswick: Tel: 0181 996 7000; Fax: 0181 996 7001.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

### **Information on standards**

BSI provides a wide range of information on national, European and international standards through its Library, the Standardline Database, the BSI Information Technology Service (BITS) and its Technical Help to Exporters Service. Contact the Information Department at Chiswick: Tel: 0181 996 7111; Fax: 0181 996 7048.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Customer Services, Membership at Chiswick: Tel: 0181 996 7002; Fax: 0181 996 7001.

### **Copyright**

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

If permission is granted, the terms may include royalty payments or a licensing agreement. Details and advice can be obtained from the Copyright Manager, BSI, 389 Chiswick High Road, London W4 4AL.

---

BSI  
389 Chiswick High Road  
London  
W4 4AL